



Rely on it.

RENOLIT SE – Plant Frankenthal

PRODUCT INFORMATION

Stretch ceiling – highgloss – 0.170mm – B-S1-d0

Type of material: Calendered PVC-film in monomeric quality, phtalhatfree, several colours specially designed for indoor – decoration with flame retardant additives.

RENOLIT description: WF-OPAK BS1D0 / WF-TRL BS1D0
Item-group: 10.40.60 / 10.40.70
Embossing: 800500 = gloss
Colour: various
Thickness: 0.170 mm

TECHNICAL DATA

Properties:	Method:	Unit:	Target:	min.:	max.:
Thickness¹	DIN EN ISO 2286-3	[mm]	0.170	0.157	0.183
Dimensional stability²	DIN 53 377	[%]	MD		- 4.0
Tensile stress at break³	DIN EN ISO 527-3/2/200	[MPa]	MD CD	20 20	
Tensile strain at break³	DIN EN ISO 527-3/2/200	[%]	MD CD	140 150	
Gloss⁴	DIN EN ISO 2813	[GU]	MD	70	
Colour⁵		[visually]	comparable with mastersample		

- 1 Measured value includes embossing, as a 2 sigma value.
- 2 10 minutes at +70°C in fan oven.
- 3 Test specimen no. 2 (15 mm width), test speed 200 mm/min – testing conditions: +23°C (± 1°C).
- 4 Measuring head 20° over a matt dark substrate.
- 5 Visually with Normlight "D65" in onelay over white substrate, angle at visual sample check in approx 45°.



Rely on it.

RENOLIT SE – Plant Frankenthal

PRODUCT INFORMATION

DEFECT ASSESSMENT

All our films are controlled by a hole-detector and additionally controlled visually. Despite all necessary care, we can't exclude defects like:

- Inclusions
- pigment contaminations
- micro-holes

Due to the production-process we are not able to exclude an „orange peel“ effect on the surface. This effect is more or less visible depending on colour.

Please also note our information-sheet "Information for processing high-gloss stretch ceiling films" before processing.

This information concerning RENOLIT products is based on the current state of our knowledge. Our products are sold under the condition that the customer ensures that the product is suitable for the type of use it is put to. All tests of technical date will be made in accordance to the above mentioned standards. This information or any parts thereof may only be published with the authorisation of RENOLIT.

This document is no technical specification or serves to replace one.

RENOLIT SE – Plant Frankenthal :

Department
Product Management

Person responsible
Nina Wachter

Issue date
October 1st 2015

Date: 10/15/ Issue: 2/ Issued by: wa- d / Info-No.: 04-00000-81

FB 7.213/S.Dengl/2-26.06.14 Produktinfo kurz Ausland

Page 2 of 2 pages

RENOLIT SE
Zweigniederlassung Frankenthal
Franz-Nissl-Straße 2
67227 Frankenthal | Germany
info@renolit.com
www.renolit.com

Sitz der Gesellschaft:
Worms
Handelsregister:
Amtsgericht Mainz
HRB 43201

Vorstand:
Michael Kundel (Vorsitzender)
Dr. Axel Bruder, Pierre Winant
Aufsichtsratsvors.: Dieter Dengl

USt-IdNr. (VAT-No.):
DE811173179

Steuer-Nr. (Fiscal-Code):
4467400058

Deutsche Bank AG, Mannheim
Sparkasse Worms-Alzey-Ried
Commerzbank AG, Worms

Kto. 037 770 500
Kto. 500 05
Kto. 387410400

BLZ 670 700 10
BLZ 553 500 10
BLZ 553 400 41

IBAN DE29 6707 0010 0037 7705 00
IBAN DE53 5535 0010 0000 0500 05
IBAN DE84 5534 0041 0387 4104 00

vinyl^{plus}



SWIFT DEUTDESM
SWIFT MALADES1W01
SWIFT COBADEFF553