

## Technical Data sheet

### RENOLIT CURPRO

Product overview | Produktübersicht | Lista de productos:

Product specifications			
Type of material:	Calandered, plasticized PVC film		
Product Name:	WF- OPAK P11 BK2 PUD4 DUNKEL GRÜN H65	Softness:	52phr/H65
Product Code:	10.60.12.0008.000	GZU product code:	FGA.GG.M094.1400
Regulation:	Reach compliant	SO#:	216975-4
Color Code:	FT77479 Dark Green	Pattern:	MJ
Property:		Thickness:	400micron

Technical properties | Technische Eigenschaften | Propiedades técnicas:

Particulars	Test Method	Unit	STD	Values
Thickness	10mm*50kpa	micron	380~430	419
Elongation @ break	ASTM D882-02	%	>200	MD:280.9    CD:283
Tensile Strength (speed: 200mm/min)	ASTM D882-02	N/mm <sup>2</sup>	>18	MD:19.3    CD:17.1
Dimensional Stability	ASTM D1204-02 (10min./80 °C)	%	<=4	1
Basis Weight		g/m <sup>2</sup>	489~541	509
Brittleness Temperature Test By Folding	DIN EN ISO 25980:2015-01	°C	Pass	Pass*
Other requirement				
Film length: 50m/roll				

MD: longitudinal, längs, longitudinal  
TD: transverse, quer, transversal



The physical properties shown above are average values obtained from tests by RENOLIT Guangzhou. All data are believed to be correct, but they do not constitute a warranty, expressed or implied, as to the condition, quality, and performance of a product for a specific use or application. The buyer or user should determine the suitability of the materials for the intended use. **RENOLIT** Guangzhou assumes no liability for any damages or consequential loss from the use of its products.

\* Based on original formula test

Test date: 05/19/2020    Tested by: Fubiao Zheng    Checked by: Shunquan Liu    Approved by: Zhihua Xue

V0 | 03/11/2022 | Page 1 de 1